



TECHNICAL BULLETIN #3135 – INSULCAST 140 FR

Date: 05/2017

PRODUCT DESCRIPTION

INSULCAST 140 FR is an epoxy casting system with high thermal conductivity. This system, when cured with **INSULCURE 11B**, also provides Class F operating properties.

PROPERTIES UNCURED

	INSULCAST 140 FR	INSULCAST 11B	
COLOR, VISUAL	Black	Amber	-
VISCOSITY, cps	220,000	700	ASTM D 2393
SPECIFIC GRAVITY	2.60	0.95	-
MIX RATIO (by wt.)	100:3-4		-
MIXED VISCOSITY @ 60°C, cps	50,000		ASTM D 2393
POT LIFE @ 25°C, hrs	2.5		-
SHELF LIFE @ 25°C, months	12		-

INSULCAST 140 FR

CASTABLE EPOXY HEAT SINK, UL RECOGNIZED UNDER FILE E86165 & MEETS THE FLAMMABILITY REQUIREMENT OF 94 V-1.

PROPERTIES CURED

PHYSICAL		
HARDNESS, DUROMETER (Shore D)	90-95	ASTM D 2393
TENSILE STRENGTH, psi	8,500	ASTM D 638
TENSILE ELONGATION, %	<1.0	ASTM D 638
COMPRESSIVE STRENGTH, psi:	18,000	ASTM D 790
FLEXURAL STRENGTH, psi:	13,500	ASTM D 790
COEFFICIENT OF THERMAL EXPANSION, °C	26x10 ⁻⁶	-
HEAT DISTORTION POINT, °C	2.3	-
CAL-CM / (CM ³) (SEC) (°C)	155	-
SERVICE TEMPERATURE, °C	-55 to +155	-

ELECTRICAL

DIELECTRIC STRENGTH, volts/mil	420	ASTM D 149
DIELECTRIC CONSTANT, 1 KHz	6.3	ASTM D 150
DISSIPATION FACTOR, 1 KHz	0.015	ASTM D 150
VOLUME RESISTIVITY, ohm-cm	1x10 ¹⁵	ASTM D 257

MIXING INSTRUCTIONS

1. Pre-heat **INSULCAST 140 FR** to 50°C to enhance flow and air release.
2. Stir contents thoroughly until all filler is dispersed.
3. Measure out required amount of **INSULCAST 140 FR**. Weigh into it 3-4 parts of **INSULCURE 11B** per 100 parts of **INSULCAST 140 FR**.
4. Mix thoroughly being sure to scrape sides and bottom of mixing container.
5. Where void-free castings are required, de-air for 2-5 minutes at 29 in. Hg.
6. Pour into mold or cavity.

CURE SCHEDULE

INSULCURE 11B **Fast Cure** - 120°C for 2 hours.
Small Mass - 95°C for 2-3 hours plus 1 hour @120°C.
Large Mass (greater than 5 lbs.) - 65°C for 4 hours plus 2 hours @120°C.

POST CURE 150°C for 4 hours
(for service temperature above 150°C).

IMPORTANT:

The following supersedes any provision in your company's forms, letters and papers. ITW ENGINEERED POLYMERS makes NO WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE FOR THIS PRODUCT. No statements or recommendations contained in the product literature are to be construed as inducements to infringe any relevant patent, now or thereafter in existence. UNDER NO CIRCUMSTANCES SHALL ITW ENGINEERED POLYMERS BE LIABLE FOR INCIDENTAL, CONSEQUENTIAL OR OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY OR ANY OTHER THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. The sole liability of ITW ENGINEERED POLYMERS for any claims arising out of the manufacture, use or sale of its products shall be to refund the buyer's purchase price, provided such products have been demonstrated in ITW ENGINEERED POLYMERS sole opinion, to justify such refund.

HEALTH CAUTION:

Avoid breathing possible fumes, mists and vapors which can cause severe respiratory damage. Use of NIOSH approved breathing apparatus is required for more than minimal exposure. Always work in areas with adequate ventilation to allow dissipation of polyamine and other chemical fumes, and where applicable, solvent fumes. Use of goggles, protective garments, rubber gloves, protective cream is required. If material gets into eyes, flush thoroughly with clean water for twenty (20) minutes; then seek medical treatment. Avoid skin contact. Material can cause contact dermatitis. Always wash exposed areas immediately, using warm water and soap, followed by rinsing with clean water. Observe all safety precautions, It is important when using solvent based materials or solvents to keep away from open flame or ignition source.

PLEASE REFER TO MATERIAL SAFETY DATA SHEET FOR FURTHER FIRST AID INFORMATION. FOR CHEMICAL EMERGENCY, CALL CHEMTREC (DAY OR NIGHT) 800 424-9300.